NESANS

TECHNICAL GUIDES


Quarry Blasting Impact on Crusher Performance: Optimize Fragment Size for Throughput

How blasting affects crusher throughput and wear. Optimize blast design for ideal fragmentation and reduce crushing costs.

Author: Sivabalan Selvarajan

Published: May 4, 2026

Reading Time: 9 minutes



The relationship between quarry blasting practices and crusher performance represents one of the most significant yet frequently overlooked optimization opportunities in aggregate production. Fragment size distribution from blasting directly impacts crusher throughput, wear costs, power consumption, and final product quality. Understanding this relationship enables plant operators to collaborate with blasting contractors for substantial production improvements.

The Blasting-Crushing Connection: Understanding the Full Impact

Every aspect of crusher operation traces back to the material delivered from the blast face. Poor fragmentation creates a cascade of problems that multiply through the entire crushing circuit, while optimized blasting can dramatically improve plant efficiency and reduce operating costs.

Fragment Size Distribution Impact on Primary Crushers

Primary jaw crushers are designed to handle specific feed size distributions. When blasting produces oversized material or excessive fines, the crusher cannot operate efficiently:

FRAGMENT CHARACTERISTIC	IMPACT ON JAW CRUSHER	OPERATIONAL CONSEQUENCE
Oversized boulders (>80% CSS)	Bridging at feed opening	Production stops, manual breaking required
Excessive fines (<25mm)	Reduced crushing efficiency	Material passes through without size reduction
Uneven size distribution	Irregular power draw	Motor overloading, inconsistent throughput
Elongated/flat fragments	Poor nip angle engagement	Material rejection, reduced capacity
Optimal 80% passing F80	Smooth crusher operation	Maximum throughput, minimal wear

Fragmentation Quality Assessment

Before adjusting blasting parameters, establish baseline fragmentation quality through systematic measurement:

Visual assessment method:

- Photograph muckpile from consistent angle and distance
- Use scale reference (1m rod) in each image
- Document oversized boulder count per blast
- Record percentage of visible fines on surface

Dig-time analysis:

- Measure excavator cycle time per bucket
- Track bucket fill factor consistency
- Document loader productivity (tonnes/hour)
- Note frequency of boulder handling delays

Software-based fragmentation analysis:

- WipFrag, Split-Desktop, or similar image analysis tools
- Provides quantitative P80, P50, uniformity index
- Enables before/after comparison of blast designs

Blasting Parameters and Their Effect on Fragmentation

Understanding how each blasting parameter affects fragment size allows for systematic optimization. Changes should be made incrementally with careful documentation of results.

Burden and Spacing Optimization

Burden (B) and spacing (S) determine energy distribution in the rock mass. The relationship between these parameters controls fragmentation uniformity:

PARAMETER RELATIONSHIP	FRAGMENTATION EFFECT	TYPICAL APPLICATION
S/B = 1.15 (tight pattern)	Finer, more uniform fragmentation	Harder rock, jaw crusher feed
S/B = 1.25 (standard)	Balanced fragmentation and cost	Medium hardness rock
S/B = 1.40 (wide pattern)	Coarser fragmentation, lower cost	Soft rock, large primary crusher

Burden calculation for Indian hard rock:

```
Burden (B) = 25 to 35 × hole diameter (mm)
For 115mm holes: B = 2.9 to 4.0 metres
Typical granite: B = 3.2 metres
Spacing = B × 1.15 to 1.25 = 3.7 to 4.0 metres
```

Explosive Energy and Powder Factor

Powder factor (kg explosive per cubic metre of rock) is the primary control for fragmentation energy. Higher powder factors produce finer fragmentation but increase blasting costs:

ROCK TYPE	POWDER FACTOR RANGE (KG/M³)	EXPECTED P80 (MM)
Soft limestone	0.25 - 0.35	400 - 500
Medium granite	0.35 - 0.50	350 - 450
Hard basalt	0.50 - 0.70	300 - 400
Very hard quartzite	0.60 - 0.85	250 - 350

Calculating optimal powder factor:

```
Volume per hole = B × S × Bench height (H)
Example: 3.2 × 3.7 × 10 = 118.4 m³

Explosive per hole = Volume × Powder factor
For granite: 118.4 × 0.45 = 53.3 kg per hole

Total explosive = Holes × kg per hole
100 holes × 53.3 = 5,330 kg per blast
```

Timing Sequence and Delay Optimization

Electronic detonators enable precise timing that dramatically improves fragmentation uniformity. Proper delay sequencing allows each row to move before subsequent rows fire:

Inter-row delay calculation:

- Minimum delay = Burden ÷ burden velocity + safety margin
- Burden velocity typically 4-6 m/ms for granite
- For 3.2m burden: 3.2 ÷ 5 = 0.64ms + 20% margin = ~10ms between rows

Electronic vs conventional timing comparison:

DETONATOR TYPE	TIMING ACCURACY	FRAGMENTATION BENEFIT	COST INCREASE
Non-electric (NONEL)	±5-10%	Baseline	-
Electronic (1ms accuracy)	±0.1%	15-25% finer P80	Rs 50-80/hole

Optimizing Fragmentation for Indian Crusher Circuits

Different crusher types have distinct fragmentation requirements. Matching blast design to your primary crusher maximizes overall circuit efficiency.

Fragmentation Targets for Jaw Crushers

Jaw crushers require specific fragment characteristics for optimal performance:

JAW CRUSHER SIZE	FEED OPENING	TARGET P80	MAXIMUM BOULDER
36×24 (900×600)	750mm	450mm	600mm
42×30 (1050×750)	900mm	550mm	700mm
48×36 (1200×900)	1000mm	650mm	850mm

Optimal jaw crusher feeding:

- 80% of material should be less than 80% of feed opening
- No material larger than 85% of feed opening

- Minimal fines (<25mm) to maximize crushing efficiency
- Cubical shape preferred over elongated fragments

Impact on Secondary and Tertiary Crushers

Primary crusher product distribution affects the entire downstream circuit:

Cascade effect of poor primary fragmentation:

1. Oversized primary product overloads secondary crusher
2. Secondary recirculation increases by 30-50%
3. Screen overloading causes blinding and carryover
4. Final product quality deteriorates
5. Overall plant capacity drops 20-40%

Economic Analysis: Blasting Cost vs Crushing Cost

The relationship between blasting investment and crushing costs follows a clear economic principle: money spent on better fragmentation almost always returns multiples in reduced crushing costs.

Cost-Benefit Calculation Framework

Example: 200 TPH aggregate plant analysis

```
Current blasting cost:
Powder factor: 0.35 kg/m³
Explosive cost: Rs 45/kg bulk emulsion
Blasting cost: 0.35 × 45 = Rs 15.75/m³
At 2.7 t/m³: Rs 5.83/tonne blasting cost

Improved blasting (higher powder factor):
Powder factor: 0.50 kg/m³
Blasting cost: 0.50 × 45 = Rs 22.50/m³
At 2.7 t/m³: Rs 8.33/tonne blasting cost
Additional cost: Rs 2.50/tonne
```

Crushing cost savings from better fragmentation:

COST CATEGORY	POOR FRAGMENTATION	OPTIMIZED FRAGMENTATION	SAVINGS
Primary crusher wear (Rs/t)	Rs 12.00	Rs 8.50	Rs 3.50
Secondary crusher wear (Rs/t)	Rs 8.00	Rs 6.00	Rs 2.00
Power consumption (Rs/t)	Rs 18.00	Rs 14.50	Rs 3.50
Maintenance labor (Rs/t)	Rs 3.50	Rs 2.50	Rs 1.00
Total savings			**Rs 10.00/t**

Net benefit: Rs 10.00 savings - Rs 2.50 additional blasting = Rs 7.50/tonne profit improvement

At 200 TPH, 10 hours/day, 300 days/year:

```
Annual production: 600,000 tonnes
Annual savings: Rs 7.50 × 600,000 = Rs 45,00,000 (Rs 45 lakhs)
```

Additional Benefits Beyond Direct Cost Savings

Optimized fragmentation delivers benefits that extend beyond immediate cost calculations:

- **Increased throughput:** 15-25% capacity improvement from smooth material flow
- **Reduced downtime:** Fewer boulder handling stops, less bridging
- **Extended equipment life:** Lower peak loads reduce fatigue damage
- **Better product quality:** More consistent gradation, improved shape
- **Lower hauling costs:** Better muckpile fragmentation improves loader productivity

Rock Mass Characterization for Blast Design

Effective blast design requires understanding the rock mass structure and properties. Different geological conditions require different approaches.

Rock Property Assessment

Key rock properties affecting fragmentation:

PROPERTY	MEASUREMENT METHOD	IMPACT ON BLAST DESIGN
Uniaxial compressive strength	Lab testing (MPa)	Higher UCS requires higher powder factor
Joint spacing	Field mapping (metres)	Closer joints allow wider burden
Joint orientation	Strike and dip measurement	Affects face stability and backbreak
Weathering grade	Visual assessment	Weathered zones need reduced charging

Adjusting for Geological Variability

Indian quarries often encounter significant geological variation. Adaptive blast design strategies:

For zones with closer joint spacing:

- Reduce powder factor by 15-25%
- Increase burden and spacing slightly
- Use smaller diameter holes if possible

For massive, tight rock zones:

- Increase powder factor by 20-30%
- Reduce burden and spacing
- Consider satellite holes for corner breaking

Practical Implementation: Working with Blasting Contractors

Effective collaboration between plant operators and blasting contractors is essential for optimization success.

Establishing Performance Metrics

Define clear, measurable targets for blast performance:

- **Fragmentation P80:** Target maximum fragment size at 80% passing
- **Oversize percentage:** Maximum acceptable boulders requiring secondary breaking
- **Fines generation:** Acceptable percentage of material below 25mm
- **Muckpile profile:** Toe position, height, spread requirements
- **Dig rate target:** Excavator productivity benchmark

Data Collection and Communication

Establish systematic feedback between crushing and blasting operations:

Daily tracking metrics:

- Primary crusher throughput (TPH actual vs rated)
- Boulder handling frequency and duration
- Power consumption per tonne
- Feeder bridging incidents

Weekly blast-to-crusher correlation:

- Match crusher performance to specific blast zones
- Document blast parameters used in each zone
- Calculate crushing cost per blast zone
- Identify best and worst performing blast designs

Common Blasting Problems and Crusher Symptoms

Learn to identify blasting issues by observing crusher behavior:

Diagnostic Table: Crusher Symptoms and Blasting Causes

CRUSHER SYMPTOM	PROBABLE BLASTING CAUSE	RECOMMENDED ACTION
Frequent bridging at feed opening	Excessive oversize from insufficient powder factor	Increase powder factor 15-20%, tighten pattern
High fines in ROM material	Over-blasting or excessive powder factor	Reduce powder factor, increase burden
Irregular power draw	Inconsistent fragment distribution	Improve timing sequence, check deck loading
Excessive jaw plate wear	High percentage of hard, blocky fragments	Optimize fragmentation for shape, not just size
Low throughput despite sized material	Elongated fragment shape causing packing	Adjust timing for better collision fragmentation

Advanced Optimization Techniques

Blast Movement Monitoring

GPS-equipped blast movement monitors (BMMs) provide precise data on rock movement during blasting, enabling more accurate post-blast ore tracking and grade control.

Vibration and Air Overpressure Control

When quarries are near communities, vibration limits may restrict blast design options. Strategies to maintain fragmentation while controlling vibration:

- Electronic detonator precision timing to reduce peak particle velocity
- Smaller holes with tighter patterns vs larger holes with wider patterns
- Deck loading to distribute energy release over time
- Pre-splitting to control backbreak and vibration direction

Implementation Checklist for Optimization Program

Phase 1: Baseline establishment (2-4 weeks)

- ☐ Document current blasting parameters and costs
- ☐ Install fragmentation photography system
- ☐ Establish crusher performance baseline metrics
- ☐ Calculate current cost per tonne breakdown

Phase 2: Trial optimization (4-8 weeks)

- ☐ Select test area with consistent geology
- ☐ Implement modified blast design (one variable at a time)
- ☐ Track crusher performance from test material
- ☐ Document cost changes and production impacts

Phase 3: Full implementation (ongoing)

- ☐ Apply optimized parameters to standard operations
- ☐ Continue monitoring and adjustment
- ☐ Develop zone-specific blast designs for geology variations
- ☐ Share results with blasting contractor for continuous improvement

By understanding the fundamental relationship between blasting and crushing, and implementing systematic optimization programs, aggregate producers can achieve significant improvements in both productivity and profitability. The investment in better blasting consistently delivers returns that far exceed the additional explosives cost.

Topics: #Blasting #Fragmentation #Jaw Crusher #Quarry Operations

NESANS
www.nesansindia.in
SF No 20/1, Eachanary Madukkarai Road, Coimbatore, TN 641024
+91 9578 799 755